

SIGMALINE 2000^{SA}

DESCRIPTION

Two-component, solvent-free, amine-cured novolac phenolic epoxy coating

PRINCIPAL CHARACTERISTICS

- One-coat system direct to metal for pipe externals
- Suitable for e.g. bell holing jobs
- Resistant to well-designed cathodic protection
- Glossy and smooth appearance
- Can be applied by heavy-duty, twin-feed, hot, airless spray equipment
- Can be applied at a substrate temperature of 90°C (194°F)
- Reduced explosion risk and fire hazard
- Meets the requirements of EN10289
- ARAMCO approved as per specification APCS 113A

COLOR AND GLOSS LEVEL

- Redbrown
- Gloss

BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	Two
Mass density	1.4 kg/l (11.7 lb/US gal)
Volume solids	100%
VOC (Supplied)	Directive 2010/75/EC, SED: max. 108.0 g/kg max. 146.0 g/l (approx. 1.2 lb/US gal)
Recommended dry film thickness	600 - 1500 µm (24.0 - 60.0 mils) depending on system
Theoretical spreading rate	1.7 m ² /l for 600 µm (67 ft ² /US gal for 24.0 mils)
Dry to touch	6 hours
Overcoating Interval	Minimum: 24 hours Maximum: 2 months
Full cure after	5 days
Shelf life	Base: at least 12 months when stored cool and dry Hardener: at least 12 months when stored cool and dry

Notes:

- See ADDITIONAL DATA – Spreading rate and film thickness
- See ADDITIONAL DATA – Overcoating intervals
- See ADDITIONAL DATA – Curing time



SIGMALINE 2000^{SA}

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

Substrate conditions

- Steel; blast cleaned to a minimum of ISO-Sa2½, blasting profile 50 – 100 µm (2.0 – 4.0 mils)
-

Substrate temperature

- Substrate temperature during application and curing should be above 5°C (41°F)
 - Substrate temperature during application and curing should be at least 3°C (5°F) above dew point
-

INSTRUCTIONS FOR USE

Mixing ratio by volume: base to hardener 78:22

- When mixing, the temperature of the base and hardener should be at least 20°C (68°F)
 - At lower temperature, the viscosity will be too high for spray application
 - No thinner should be added
-

Induction time

None

Pot life

1 hour at 20°C (68°F)

Note: See ADDITIONAL DATA – Pot life

Airless spray

Recommended thinner
No thinner should be added

Nozzle orifice
Approx. 0.53 mm (0.021 in)

Nozzle pressure
At 20°C (68°F) paint temperature min. 28.0 MPa (approx. 280 bar; 4061 p.s.i.). At 30°C (86°F) min. 22.0 MPa (approx. 220 bar; 3191 p.s.i.)

Notes:

- Use heavy-duty, single-feed, airless spray equipment, preferably 60:1 pump ratio and suitable high-pressure hoses
 - In-line heating or insulated hoses may be necessary to avoid cooling down of paint in hoses at low air temperature
 - Length of hoses should be as short as possible
-

SIGMALINE 2000^{SA}

Brush/roller

- For stripe coating and spot repair only

Recommended thinner

No thinner should be added

Cleaning solvent

THINNER 90-53 or THINNER 90-83

Note: All application equipment must be cleaned immediately after use. Paint inside the spraying equipment must be removed before the pot life has been expired.

ADDITIONAL DATA

Spreading rate and film thickness	
DFT	Theoretical spreading rate
600 µm (24.0 mils)	1.7 m ² /l (67 ft ² /US gal)
1000 µm (40.0 mils)	1.0 m ² /l (40 ft ² /US gal)
1500 µm (60.0 mils)	0.7 m ² /l (27 ft ² /US gal)

Note: Maximum DFT when brushing: 150 µm (6.0 mils)

Measuring wet film thickness

- A deviation is often obtained between the measured apparent WFT and the real applied WFT
- A difference is often obtained between the measured apparent WFT and the real applied WFT. This is due to the thixotropy and the surface tension of the paint, which retards the release of air, trapped in the paint film for some time
- Recommendation is to apply a WFT, which is equal to the specified DFT plus 60 µm (2.4 mils)

Maximum dry film thickness

- Because of low initial hardness the DFT cannot be measured within some days, due to the penetration of the measuring device into the soft paint film
- The DFT should be measured using a calibration foil of known thickness placed in between the coating and the measuring device

Overcoating interval for DFT up to 600 µm (24.0 mils)					
Overcoating with...	Interval	5°C (41°F)	10°C (50°F)	20°C (68°F)	30°C (86°F)
itself for repair only	Minimum	3.5 days	36 hours	24 hours	12 hours
	Maximum	3 months	3 months	2 months	1 month

Note: Surface should be dry and free from any contamination



SIGMALINE 2000^{SA}

Curing time for DFT up to 600 µm (24.0 mils)

Substrate temperature	Dry to handle	Full cure
5°C (41°F)	60 hours	15 days
10°C (50°F)	30 hours	7 days
20°C (68°F)	16 hours	5 days
30°C (86°F)	10 hours	3 days

Note: Adequate ventilation must be maintained during application and curing (please refer to INFORMATION SHEETS 1433 and 1434)

Pot life (at application viscosity)

Mixed product temperature	Pot life
20°C (68°F)	1 hour
30°C (86°F)	45 minutes
40°C (104°F)	20 minutes

Notes:

- Due to exothermic reaction, temperature during and after mixing may increase
- It is recommended to use plural airless equipment due to the short pot life when paint temperature is above 40°C (104°F)

SAFETY PRECAUTIONS

- For paint and recommended thinners see INFORMATION SHEETS 1430, 1431 and relevant Material Safety Data Sheets
- Although this is a solvent-free paint, care should be taken to avoid inhalation of spray mist, as well as contact between the wet paint and exposed skin or eyes
- Ventilation should be provided in confined spaces to maintain good visibility

WORLDWIDE AVAILABILITY

It is always the aim of Sigma Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

SIGMALINE 2000^{SA}

REFERENCES

• CONVERSION TABLES	INFORMATION SHEET	1410
• EXPLANATION TO PRODUCT DATA SHEETS	INFORMATION SHEET	1411
• SAFETY INDICATIONS	INFORMATION SHEET	1430
• SAFETY IN CONFINED SPACES AND HEALTH SAFETY, EXPLOSION HAZARD – TOXIC HAZARD	INFORMATION SHEET	1431
• CLEANING OF STEEL AND REMOVAL OF RUST	INFORMATION SHEET	1490
• SPECIFICATION FOR MINERAL ABRASIVES	INFORMATION SHEET	1491
• SURFACE PREPARATION OF STEEL PIPES AND FITTINGS SHOP APPLICATION	INFORMATION SHEET	1492
• INTERNAL CHEMICAL CLEANING OF STEEL PIPES IN-SITU APPLICATION	INFORMATION SHEET	1493
• RELATIVE HUMIDITY – SUBSTRATE TEMPERATURE – AIR TEMPERATURE	INFORMATION SHEET	1650

WARRANTY

Sigma warrants (i) its title to the product, (ii) that the quality of the product conforms to Sigma’s specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT SIGMA MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY SIGMA. Any claim under this warranty must be made by Buyer to Sigma in writing within five (5) days of Buyer’s discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer’s failure to notify Sigma of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL SIGMA BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that Sigma believes to be reliable. Sigma may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the Sigma product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of Sigma’s knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user’s responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. Sigma has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, Sigma does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer’s responsibility to ensure that this information is current prior to using the product. Current sheets for all Sigma Protective & Marine Coatings Products are maintained at www.sigmaint.com. The English text of this sheet shall prevail over any translation thereof.

